

Physical Properties (Silt Fence)

| Properties ¹ | Test Method | Unit | ET70SF | ET80SF | ET90SF | ET100SF |
|--|--------------------|-----------------------------|-----------------|-----------------|-----------------|-----------------|
| Tensile Strength | ASTM D-4632 | lbs | † 120 x 95 | † 120 x 100 | † 130 x 120 | † 135 x 125 |
| Elongation | ASTM D-4632 | % | 24 | 24 | 30 | 15 |
| Trapezoidal Tear | ASTM D-4533 | lbs | 60 | 60 | 60 | 60 |
| Apparent Opening Size² | ASTM D-4751 | U.S. Sieve | 25 | 25 | 30 | 30 |
| Water Flow Rate | ASTM D-4491 | gpm / ft² | 5 | 6 | 8 | 10 |
| UV Stability (@ 500hrs) | ASTM D-4355 | % | 80 | 80 | 80 | 80 |
| Roll Dimensions | | | | | | |
| Roll Width^{***} | | inches | 32" / 36" | 32" / 36" | 32" / 36" | 32" / 36" |
| Roll Length^{***} | | ft | 3,330' | 3,330' | 3,330' | 3,330' |
| Roll Area^{***} | | yds² | 978sy / 1,100sy | 978sy / 1,100sy | 978sy / 1,100sy | 978sy / 1,100sy |

1 : Minimum Average Roll Value (MARV)

2 : Maximum Average Roll Value

† : Typical Roll Properties

*** Custom roll sizes available

*** Custom colors and striping available

*** Other GSM can be provided on request

Rights are reserved to modify the present data sheet without prior notice

Information deemed to be accurate but not guaranteed